



Inspection Report

Sample:

Inspection Sort



Henan Institute of

National Center for Quality Inspection of

委托单位	蒙娜丽莎集团股份有限公司	联系电话	
生产日期	2024-11-20	抽样地点	产品批号
抽样基数/批量		样品数量	检验日期
样品状态 Sample State	样品外观完好		
主要设备	YJC0D01800	数显陶瓷砖吸水率煮沸试验装	

河南省产品质量检验技术研究院

国家建筑装修材料质量检验检测中心

检验检测报告

№：202520000

№	Items	Unit	Standards	Specification	Test Data	Conclusion
2	表面质量	/	GB/T3810.2-2016	不少于95%的砖表面无可见缺陷	主要区域无可见缺陷	符合
3	长度	mm	GB/T3810.2-2016	1200(1±0.6%) 最大值±2.0	1199.8～1199.9	符合
4	宽度	mm	GB/T3810.2-2016	600(1±0.6%)，最大值±0.6	599.7～599.9	符合
5	厚度	mm	GB/T3810.2-2016	9(1±4%)，最大值±0.5	9.0～9.1	符合
6	直角度	%	GB/T3810.2-2016	±0.5	-0.03～-0.01	符合
7	平面度	%	GB/T3810.2-2016	±0.5	-0.03～-0.01	符合
8	边直度	%	GB/T3810.2-2016	±0.5	-0.03～-0.01	符合
9	中心弯曲度	%	GB/T3810.2-2016	±0.5	-0.03～-0.01	符合
10	单个值	MPa	GB/T3810.4-2016	≥32	36～38	符合
11	破坏强度	平均值	GB/T3810.4-2016	≥29	34	符合
12	抗冻性	/	GB/T3810.12-2016	经试验应无裂纹	未见裂纹及剥落	符合
13	耐磨性	干法	GB/T14100-2015 附录M	≥0.50	0.66	符合
		湿法		≥0.50	0.64	符合
14	耐污染性	有釉砖	GB/T3810.14-2016	最低3级	5级	符合

河南省产品质量检验技术研究院

No	Items	Unit	Standards	Specification	Test Data	Conclu
	内照射指					
22	湿膨胀	mm/m	GB/T3810.10-2016	/	0.10	

注 意 事 项

1. 报告无我单位“检验检测专用章”和[illegible]

Notice

1. The report is inv[illegible]ould. The Special Seal for "Inspection and Testing", and w
ithout the signatures of Editor or Chief Inspector, Verifier, Appr[illegible]

[illegible]superior department[illegible]

[illegible]ave any question on the reports, please submit to our unit, to t
to the administration department which decided the i[illegible]
days) after receiv[illegible]

[illegible]

[illegible]